



GRT.0252

GROUT FILL

Castable cement micromortar,
for paving in natural stone

Customs Code

3824 5090

Packaging

- Bag 25 kg
- Pallet: 50 x (Bag 25 kg)

Application

- Pour out

Family
Grout

Product Lines

- Building
- Floor

Components
Single-component

Type

Fluid grouts and micro mortars with a cement base

Functional Categories

- Block repair of concrete works with free-flowing mortars
- Roads and municipal maintenance interventions
- Structural precision anchoring

Appearance

Powder

General description

An anti-shrinkage, pourable, self-levelling, super-adhesive micro-mortar, based on high-strength cements, super-pozzolanic fillers, polymeric stabilisers and anti-shrinkage agents. Aggregates with a maximum size of 0.35 mm. Ideal for filling joints (gaps and/or interstices) in urban paving made of porphyry or stone slabs, even of large dimensions. For filling cracks and lesions on concrete and masonry structures.






General features

GROUT FILL achieves fluid and hyperfluid workability even with very low water / cement ratios (<0.4), thus resulting perfectly homogeneous, pourable, self-leveling and without water exudation phenomena. The very fine granulometry of the aggregates allows the perfect filling of spaces and particularly narrow discontinuities (<0.5 cm). The capillary absorption of the applied micro-mortar is very low, allowing great resistance to freeze-thaw cycles and washout. GROUT FILL achieves extremely high mechanical performance and is rich in microsilicates with pozzolanic activity and special additives that make it extremely durable even if positioned in particularly aggressive environments (due to contamination by chlorides, sulphates, marine atmospheres, fuels and automotive oils).

Fields of application

Filling the joints (vanishing points) in urban floorings in porphyry, stone slabs etc., in new installations and in the reinforcement of existing installations. Anchorages and rigid seals in general.

Basic features

- | | |
|---|---|
|  Maximum diameter of aggregate:
0.35 mm |  Pot-life:
60 min |
|  Shelf-life:
12 months |  Temperature of use:
+5/+35 °C |
|  Available colours
Gray | |

Technical specifications

Bonding force (UNI EN 1015-12): > 2.5 N/mm²

Capillary absorption (UNI EN 13057): 0.08 kg/(m² • h^{0.5})

Chloride content (UNI EN 1542): 0.002 %

Compressive strength after 01 day (UNI EN 1015-11): > 35 N/mm²

Compressive strength after 07 days (UNI EN 1015-11): > 65 N/mm²

Compressive strength after 28 days (UNI EN 1015-11): > 80 N/mm²

Darcy impermeability: 10⁻¹⁰ cm/s

Density (UNI EN 1015-6): 2250 kg/m³

Flexural strength after 07 days (UNI EN 1015-11): > 11 N/mm²

Flexural strength after 28 days (UNI EN 1015-11): > 13 N/mm²

Flexural strength at 01 day (UNI EN 1015-11): > 8 N/mm²

No bleeding according to UNI 8998

pH: > 12 _

IF YOU WANT TO SOLVE IT
 azichem

www.azichem.com

Updated: 29/11/2021

General sales conditions and legal
notices on
www.azichem.com/disclaimer

Tools cleansing

- Water

Applicable on

- Concrete
- Floor screed
- Asphalt
- Porphyry and natural stones

Instructions for use

Pour about 2/3 of the required mixture water in the mixer (about 3.5 -4 litres total per bag); gradually add the product and the water still required to get the desired consistency. Continue mixing until you obtain a homogeneous, lump-free mortar. Pour the compound thus obtained in the vanishing points to be filled.

Substrate preparation

Remove the soilings, the crumbling and non-adhering parts and saturate beforehand with water.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



Warnings, Precautions and Ecology

The general information, along with any instructions and recommendations for use of this product, including in this data sheet and eventually provided verbally or in writing, correspond to the present state of our scientific and practical knowledge.

Any technical and performance data reported is the result of laboratory tests conducted in a controlled environment and thus may be subject to modification in relation to the actual conditions of implementation.

Azichem Srl does not assume any liability arising from inadequate characteristics related to improper use of the product or connected to defects arising from factors or elements unrelated to the quality of the product, including improper storage.

Those wishing to utilise the product are required to determine prior to use whether or not the same is suitable for the intended use, assuming all consequent responsibility.

The technical and characteristic details contained in this data sheet shall be updated periodically. For consultation in real time, please visit the website: www.azichem.com. The date of revision is indicated in the space to the side. The current edition cancels out and replaces any previous version.

Please note that the user is required to read the latest Safety Data Sheet for this product, containing chemical-physical and toxicological data, risk phrases and other information regarding the safe transport, use and disposal of the product and its packaging. For consultation, please visit: www.azichem.com.

It is forbidden to dispose of the product and/or packaging in the environment.

Do not apply in the presence of stagnant water and direct solar irradiation, in anticipation of atmospheric precipitation and/or sudden drops in temperature.

Treat the hardening and the damp protection fresh mortar placed on site .



www.azichem.com

Updated: **29/11/2021**
General sales conditions and legal notices on www.azichem.com/disclaimer

GROUTFILL is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **29/11/2021**
General sales conditions and legal
notices on
www.azichem.com/disclaimer

Page: **3/3**